SOFT-MAGNETIC ALLOYS

Magfield 77 Nickel-Iron Soft-Magnetic Alloy

W.N.: 2.4530 DIN: NiFe16CuMo

UNS: -//-

Magfield 77

Magfield 77 is a nickel-iron soft-magnetic alloy with Ni content about 77%, additionally alloyed by 4% of Mo and 5.5% of Cu.

Magfield 77 is characterized by high permeability and good formability.

Applications: cores of pulse transformers, magnetic amplifiers, relays, LF transducers, high metering accuracy (HMA) cores, laminations, shielding, etc.

1. Chemical composition

Nominal composition, %	С	Р	S	Mn	Si	Мо	Сυ	Fe	Ni
min	-	-	-	-	-	3.90	4.80	12.00	D. I
max	0.03	0.02	0.02	0.60	0.30	4.50	6.00	16.00	Bal.

2. Mechanical properties

Condition	Yield Strength, R _{p0.2} (MPa)	Tensile Strength, R _m (MPa)	Hardness, HV	Elongation, A (%)
soft, annealed	320	630	160	≥ 40

3. Magnetic properties

Saturation Bs, T	0.75
Coercivity Hc, A/m	≤1.40

Initial permeability $\mu_{\scriptscriptstyle 0.80}$,mH/m	≥31.80	
Maximum permeability µ _{max} ,mH/m	≥225.00	

4. Physical properties

Density, g/cm³	8.60
Electrical resistivity at 20°C, Ω mm²/m	0.55
Thermal conductivity at 20°C, W/mk	17.00
Melting point, °C	1450
Curie point, °C	350

	100°C	10.30
Coefficient of thermal	200°C	10.90
expansion, 10 ⁻⁶ /K	300°C	11.40
	400°C	11.90
	500°C	12.50

5. Delivery form, dimensions, condition.

Form*	Thickness, mm	Width, mm	Length, mm	Finish
Strip/Coil	0.10-2.50	10.00 - 400.00	-	soft annealed / hard
Sheet	0.50-3.50	5.00 - 400.00	500.00 - 3500.00	soft anneled / hard

^{*}Other dimensions and specifications upon request.

Note: All information enclosed in this datasheet is based on our best knowledge and is given as indicative. Other special requirements are subject to prior discussion and approval of Vojay. Please contact us for any additional information or request.

